

C69700

SILICON BRASS

DESCRIPTION

C69700 brass is a brass formulated for primary forming into wrought products. It is typically furnished in the H04 (full hard) temper. It has a moderately low melting temperature and a fairly high tensile strength relative to other wrought brasses.

CHEMICAL COMPOSITION

Elements	Min (%)	Max (%)
Cu	75.00	80.00
Pb	0.50	1.50
Fe	-	0.20
Mn	-	0.40
Si	2.50	3.50
Total Others	-	0.50
Zn	Remainder	

MECHANICAL PROPERTIES ACCORDING TO ASTM B371 (AS PER TEMPER Ho2)

Range (Inch)	From	To	UTS Min (ksi)	PS Min (Ksi)	Elongation Min (%)	Hardness Min	Hardness Max
Round (Dia)	0.059	1.000	65	32	20	-	-
	1.000		55	28	25	-	-
Hex (A/F)	0.118		65	32	20	-	-
	1.000	2.755	55	28	25	-	-
Square (A/F)	0.118	1.000	65	32	20	-	-
	1.000	2.362	55	28	25	-	-



C69700

SILICON BRASS

Range (mm)	From	To	UTS Min (Mpa)	PS Min (Mpa)	Elongation Min (%)	Hardness Min	Hardness Max
Round (Dia)	1.5	25	450	220	20	-	-
	25	75	380	195	25	-	-
Hex (A/F)	3	25	450	220	20	-	-
	25	70	380	195	25	-	-
Square (A/F)	3	25	450	220	20	-	-
	25	60	380	195	25	-	-

PHYSICAL PROPERTIES

No physical properties for this alloy

FABRICATION PROPERTIES

Technique	Suitability
Machinability Rating	70

TYPICAL USES

- Valves Stems

