

C36000

FREE MACHINING BRASS

DESCRIPTION

36000 (HO2) Free machining brass, produced from a combination of copper and zinc, has the highest machinability of all copper alloys, and is the standard against which all the others are compared to. 360 Brass, known for its strength and resistance to corrosion with properties closely resembling that of steel, is one of the most popular copper alloys used today. 360 Brass can be precision machined easily. Although ductile in its softened state, 360 Brass is a strong material to work with and maintains its strength even under some of the most demanding conditions. 360 Brass forms a thin protective "patina", which, unlike steel and iron, will not rust when exposed to the atmosphere. As a high-density material, 360 Brass is ideal for heavy industrial parts. 360 Brass is also valued for its high polished finish. 360 Brass is available in rounds, flats, squares, hexagons, tube, plate, and sheet.

CHEMICAL COMPOSITION

Elements	Min (%)	Max (%)
Cu	60.00	63.00
Pb	2.50	3.00
Fe	-	0.35
Total others	-	0.50
Zn	Remainder	

C36000

FREE MACHINING BRASS

MECHANICAL PROPERTIES (AS PER TEMPER HO2)

Range (Inch)		From	To	UTS Min (Ksi)	PS Min (Ksi)	Elongation Min (%)	Hardness Min (HRB)	Hardness Max (HRB)
Round (Dia)		0.059	0.500	57.00	25.00	7.00	-	-
		0.500	1.000	55.00	25.00	10.00	60.00	80.00
		1.000	2.000	50.00	20.00	15.00	55.00	75.00
		2.000	2.953	45.00	15.00	20.00	45.00	70.00
Hex (A/F)		0.118	0.500	57.00	25.00	7.00	-	-
		0.500	1.000	55.00	25.00	10.00	55.00	80.00
		1.000	2.000	50.00	20.00	15.00	45.00	80.00
		2.000	2.756	45.00	15.00	20.00	40.00	65.00
Square (A/F)		0.118	0.500	57.00	25.00	7.00	-	-
		0.500	1.000	55.00	25.00	10.00	55.00	80.00
		1.000	2.000	50.00	20.00	15.00	45.00	80.00
		2.000	2.362	45.00	15.00	20.00	40.00	65.00
Octagon (A/F)		0.118	0.500	57.00	25.00	7.00	-	-
		0.500	1.000	55.00	25.00	10.00	55.00	80.00
		1.000	2.000	50.00	20.00	15.00	45.00	80.00
		2.000	2.362	45.00	15.00	20.00	40.00	65.00
Rectangle	Thickness	0.118	0.500	50.00	25.00	10.00	45.00	85.00
	Width	0.118	1.000					
	Thickness	0.118	0.500	45.00	17.00	15.00	35.00	70.00
	Width	1.000	2.756					
	Thickness	0.500	1.969	45.00	17.00	15.00	40.00	80.00
	Width	0.079	2.000					
	Thickness	0.500	1.968	40.00	15.00	20.00	35.00	70.00
	Width	2.000	2.756					

C36000

FREE MACHINING BRASS

MECHANICAL PROPERTIES (AS PER TEMPER HO2)

Range (mm)		From	To	UTS Min (MPa)	PS Min (MPa)	Elongation Min (%)	Hardness Min (HRB)	Hardness Max (HRB)
Round (Dia)		1.5	12.00	395.00	170.00	7.00	-	-
		12.00	25.00	380.00	170.00	10.00	60.00	80.00
		25.00	50.00	345.00	140.00	15.00	55.00	75.00
		50.00	75.00	310.00	105.00	20.00	45.00	70.00
Hex (A/F)		3.00	12.00	395.00	170.00	7.00	-	-
		12.00	25.00	380.00	170.00	10.00	55.00	80.00
		25.00	50.00	345.00	140.00	14.00	45.00	80.00
		50.00	70.00	310.00	105.00	20.00	40.00	65.00
Square (A/F)		3.00	12.00	395.00	170.00	7.00	-	-
		12.00	25.00	380.00	170.00	10.00	55.00	80.00
		25.00	50.00	345.00	140.00	15.00	45.00	80.00
		50.00	60.00	310.00	105.00	20.00	40.00	65.00
Octagon (A/F)		3.00	12.00	395.00	170.00	7.00	-	-
		12.00	25.00	380.00	170.00	10.00	55.00	80.00
		25.00	50.00	345.00	140.00	15.00	45.00	80.00
		50.00	60.00	310.00	105.00	20.00	40.00	65.00
Rectangle	Thickness	3.00	12.00	345.00	170.00	10.00	45.00	85.00
	Width	4.00	25.00					
	Thickness	3.00	12.00	310.00	115.00	15.00	35.00	70.00
	Width	25.00	70.00					
	Thickness	12.00	50.00	310.00	115.00	15.00	40.00	80.00
	Width	4.00	50.00					
	Thickness	12.00	50.00	275.00	105.00	20.00	35.00	70.00
	Width	50.00	70.00					

C36000

FREE MACHINING BRASS

PHYSICAL PROPERTIES

Melting Point - Liquidus°F	1650
Melting Point - Solidus°F	1630
Densitylb/cu in. at 68°F	0.307
Specific Gravity	8.5
Electrical Conductivity% IACS at 68°F	26
Thermal ConductivityBtu/ sq ft/ ft hr/ °F at 68°F	67
Coefficient of Thermal Expansion 68-57210- ⁶ per °F (68 – 572°F)	11.4
Specific Heat CapacityBtu/ lb /°F at 68°F	0.09
Modulus of Elasticity in Tensionksi	14000
Modulus of Rigidityksi	5300

FABRICATION PROPERTIES

Melting Point - Liquidus°F	1650
Melting Point - Solidus°F	1630
Densitylb/cu in. at 68°F	0.307
Specific Gravity	8.5
Electrical Conductivity% IACS at 68°F	26
Thermal ConductivityBtu/ sq ft/ ft hr/ °F at 68°F	67
Coefficient of Thermal Expansion 68-57210- ⁶ per °F (68 – 572°F)	11.4
Specific Heat CapacityBtu/ lb /°F at 68°F	0.09
Modulus of Elasticity in Tensionksi	14000
Modulus of Rigidityksi	5300
Machinability Rating	100

TYPICAL USES

- Automotive
- Builders Hardware
- Consumer
- Fasteners
- Industrial
- Plumbing