

CZ119

LEADED BRASS

DESCRIPTION

CZ119 are the standard materials for machining (machining index 100 %). These alloys are also particularly suitable for hot stamping when the forged parts are subsequently machined extensively. Is recommended for applications where cold working with little reduction such as knurling is used. The ductility of this material makes it particularly suitable for the manufacture of wires as well as rods and sections.

CHEMICAL COMPOSITION

Elements	Min (%)	Max (%)
Cu	61.00	64.00
Pb	1.00	2.50
Total Others Incl Fe	-	0.30
Zn	Remainder	

MECHANICAL PROPERTIES (AS PER TEMPER M)

Range (mm)	From	To	UTS Min (N/mm ²)	PS Min (N/mm ²)	Elongation Min (%)	Hardness Min (HV)	Hardness Max
Round (Dia)	1.5	75.00	340.00	-	15.00	90.00	-
Hex (A/F)	3.00	70.00	340.00	-	15.00	90.00	-
Square (A/F)	3.00	60.00	340.00	-	15.00	90.00	-
Rectangle (Thickness)	3.00	50.00	340.00	-	15.00	90.00	-

CZ119

LEADED BRASS

PHYSICAL PROPERTIES

Melting Point - Liquidus°F	1700
Melting Point - Solidus°F	1630
Densitylb/cu in. at 68°F	0.306
Specific Gravity	8.47
Electrical Conductivity% IACS at 68°F	26
Thermal ConductivityBtu/ sq ft/ ft hr/ °F at 68°F	67
Coefficient of Thermal Expansion 68-57210 ⁻⁶ per °F (68 – 572°F)	11.3
Specific Heat CapacityBtu/ lb /°F at 68°F	0.09
Modulus of Elasticity in Tensionksi	15000
Modulus of Rigidityksi	5600

FABRICATION PROPERTIES

Technique	Suitability
Soldering	Excellent
Brazing	Good
Oxyacetylene Welding	Not Recommended
Gas Shielded Arc Welding	Not Recommended
Coated Metal Arc Welding	Not Recommended
Not Recommended	Not Recommended
Seam Weld	Not Recommended
Butt Weld	Fair
Capacity for Being Cold Worked	Good
Capacity for Being Hot Formed	Poor
Machinability Rating	85%

TYPICAL USES

- Automotive
- Builders Hardware
- Consumer
- Electrical
- Fasteners
- Industrial
- Ordnance
- Plumbing